

# **PREMCOTE P27 PRIMER**

**Butyl Tape Primer**

## **Description**

Premcote P27 Primer is a quick drying, solvent based, high-tack primer specifically designed to promote maximum adhesion.

## **Uses**

A fast drying butyl based primer for all surfaces prior to the application of various Premier Butyl tapes.

## **Features**

- Fills surface irregularities for intimate contact of tape compound
- Promotes high adhesion
- Fast drying
- Good penetration characteristics
- Can be brush or spray applied

## **Application**

Prepare surfaces by removing all loose scale, rust or other foreign matter by grit blasting or wire brush. Apply a thin uniform coat of Premier Butyl Primer to clean surface and allow to tack dry. Prime only areas to be wrapped the same day. Reprime if area becomes dirty or wet.

# Premcote P27 Primer

## PROPERTY SPECIFICATIONS

PROPERTIES	ENGLISH
% Solids	46% by wt.
Viscosity @ 73°F (23°C)	200 cps
VOC	450 g/l
Minimum Application Temperature	25°F (-4°C)
Coverage	245 ft <sup>2</sup> /Gal (22.76 m <sup>2</sup> /liters)
Color	Blue

### COVERAGE:

366 ft<sup>2</sup> per case - 1 quart containers  
(33 m<sup>2</sup> liters per case - 1.0 liter containers)

980 ft<sup>2</sup> per case - 1 gallon containers  
(90 m<sup>2</sup> liters per case - 4 liter containers)

### PACKAGING:

6 each 1 quart containers per case  
(6 each 1.00 liter containers per case)

4 each 1 gallon containers per case  
(4 each 4 liter containers per case)



**HOUSTON:**  
9747 Whithorn Drive,  
Houston, Texas,  
U.S.A. 77095  
Tel: 1-281-821-3355  
Fax: 1-281-821-0304

**TORONTO:**  
90 Ironside Crescent,  
Unit 12, Toronto,  
Ontario, Canada M1X1M3  
Tel: 1-416-291-3435  
Fax: 1-416-291-0898

e-mail: [info@premiercoatings.com](mailto:info@premiercoatings.com)

[www.premiercoatings.com](http://www.premiercoatings.com)

***A Member of Winn & Coales International***

The information given on this sheet is intended as a general guide only and should not be used for specification purposes. We believe the information to be accurate and reliable but do not guarantee it. We assume no responsibility for the use of this information. Users must, by their own tests, determine the suitability of the products and information supplied by us for their own particular purposes. No patent liability can be assumed.